

REV. 2025.1 · 2025 EDITION

Installation guide · Large-format slabs

Handling, adhesives, double-buttering, joints and on-site cutting.

CERAMIC SLABS

INSTALLATION

- Handle slabs with suction cups and frame; never upright without continuous support.
- Apply double-buttering with C2TE S1 adhesive and a 10 mm notched trowel on substrate and piece.
- Respect a minimum 2 mm joint indoors and expansion joints every 25 m² or 6 linear metres.
- On-site cuts are made with a water-cooled continuous diamond disc.

CARE & MAINTENANCE

- Daily cleaning with warm water and neutral detergent; rinse and dry to avoid limescale marks.
- Avoid strong acids (hydrofluoric) and metal scourers on polished finishes.
- Dried stains are removed with an alkaline cleaner and a soft-bristle brush.